

STATE OF NORTH CAROLINA DEPARTMENT OF TRANSPORTATION

BEVERLY EAVES PERDUE
GOVERNOR

EUGENE A. CONTI, JR. SECRETARY

March 13, 2012

Addendum No. 1

RE: Contract ID C202976 WBS # 17BP.6.P.2

Bladen, Robeson, Cumberland Counties

Bridge #4 on NC-130, #13 on SR-1207, #70 &72 on US-74, #96 on SR-1155, #106 &107 on I-95, #17 on US-701 and #147 on SR-1832

March 20, 2012 Letting

To Whom It May Concern:

Reference is made to the plans and proposal furnished to you on this project.

The following revisions have been made to the plans:

Sheet Nos. S-7, S-8, S-9, S-15, S-16 and S-17 have been revised to change "latex modified concrete" to "latex modified concrete-very early strength". Please void Sheet Nos. S-7, S-8, S-9, S-15, S-16 and S-17 in your plans and staple the revised Sheet Nos. S-7, S-8, S-9, S-15, S-16 and S-17 thereto.

On Sheet No. S-41, Detail "A" has been removed. Please void Sheet No. S-41 in your plans and staple the revised Sheet No. S-41 thereto.

On Sheet No. S-44, Detail "D" has been revised. Please void Sheet No. S-44 in your plans and staple the revised Sheet No. S-44 thereto.

The following revisions have been made to the Proposal:

On Page No. 65 the paragraph titled "Past Performance Submittal" has been revised. Please void Page No. 65 in your proposal and staple the revised Page No. 65 thereto.

1591 MAIL SERVICE CENTER
RALEIGH NC 27699-1591

TELEPHONE: 919-707-6900 FAX: 919-250-4119 WEBSITE: WWW.NCDOT.ORG LOCATION: CENTURY CENTER COMPLEX ENTRANCE B-2 1020 BIRCH RIDGE DRIVE RALEIGH NC 27610 On Page No. 2 of the item sheets the following pay item quantities have been revised:

<u>Item</u>	Description	Old Quantity	New Quantity
27-8881000000-E-SP	Latex Modified Concrete Overlay	167.9 CY	108.8 CY
28-881000000-E-SP	Latex Modified Concrete Overlay-Very Early Strength	83.1 CY	142.2 CY
32-8893000000-E-SP	Placing and Finishing Latex Modified Concrete Overlay	3,618.8 SY	2,195.4 SY
33-8893000000-E-SP	Placing and Finishing Latex Modified Concrete Overlay-Very Early Strength	1,962.4 SY	3,385.8 SY

The Contractor's bid must be based on these revised pay item quantities. The contract will be prepared accordingly.

The Expedite File has been updated to reflect these revisions. Please download the Expedite Addendum File and follow the instructions for applying the addendum. Bid Express will not accept your bid unless the addendum has been applied.

Sincerely,

R. A. Garris, PE Contract Officer

RAG/jag Attachments

cc:	Mr. Jon Nance, PE	Mr. R.E. Davenport, PE
	Mr. Ron Hancock, PE	Ms. Natalie Roskam, PE
	Mr. G. W. Burns, PE	Mr. G.R. Perfetti, PE
	Ms. D. M. Barbour, PE	Mr. Ronnie Higgins
	Mr. J. V. Barbour, PE	Mr. Larry Strickland
	Ms. Penny Higgins	Ms. Marsha Sample
	Ms. Lori Strickland	Ms. Jaci Kincaid
	Project File (2)	

Revised 3-13-12

Submit the latex modified concrete mix design, including laboratory compressive strength data for a minimum of six 4-inch by 8-inch cylinders at the appropriate age (7 days for normal setting concrete; 3 hours for very early strength concrete) to the Engineer for review. Include test results for the slump and air content of the laboratory mix. Perform tests in accordance with AASHTO T 22, T 119 and T 152.

System Quality Submittals

Past Performance Submittal: At the preconstruction conference, the latex modified concrete overlay Contractor shall submit verifiable records demonstrating that he or his approved subcontractor has performed satisfactorily, or that he has had direct supervision of such satisfactory performance of a sub-contractor constructing contracts using very early strength latex modified concrete. At least five (5) bridges with similar scope of work in any state shall be the minimum number demonstrated.

Construction Methods

(A) <u>Preparation of Surface</u>

Completely clean all surfaces within the 48 hours prior to placing the overlay unless otherwise approved.

Thoroughly soak the clean surface for at least 2 hours immediately prior to placing the latex modified concrete. After soaking the surface for at least 2 hours, cover it with a layer of white opaque polyethylene film that is at least 4 mils (0.100 mm) thick. Immediately prior to placing the latex modified concrete, remove standing water from the surface.

(B) Placing and Finishing

Prior to placing modified material, install a bulkhead of easily compressible material at expansion joints to the required grade and profile. Placing material across expansion joints and sawing it later is not permitted.

Place and fasten screed rails in position to ensure finishing the new surface to the required profile. Do not treat screed rails with parting compound to facilitate their removal. Prior to placing the overlay, attach a filler block sized for the plan overlay thickness to the bottom of the screed and pass it over the area to be repaired to check the thickness. Remove all concrete that the block does not clear.

Separate screed rails or construction dams from the newly placed material by passing a pointing trowel along their inside face. Carefully make this trowel cut for the entire depth and length of rails or dams after the modified composition has sufficiently stiffened and cannot flow back.

Brush a latex cement mixture onto the wetted, prepared surface. Carefully give all vertical and horizontal surfaces a thorough, even coating and do not let the brushed material dry before it is covered with the additional material required for the final grade. Remove all loose aggregate from the latex cement brushed surface prior to latex concrete placement (NOTE: Not required for surfaces prepared with hydro-demolition).

Place the latex modified concrete in one operation.