## **PROJECT SPECIAL PROVISIONS**

## **ROADWAY**

MATERIALS: (2-21-12) (Rev. 5-21-13)

1000, 1005, 1050, 1074, 1078, 1080, 1081, 1087, 1092

SP10 R01

Revise the 2012 Standard Specifications as follows:

## Page 10-1, Article 1000-1, DESCRIPTION, line 14, add the following:

Use materials which do not produce a mottled appearance through rusting or other staining of the finished concrete surface.

Page 10-5, Table 1000-1, REQUIREMENTS FOR CONCRETE, replace with the following:

TABLE 1000-1 REQUIREMENTS FOR CONCRETE												
Class of Concrete	Min. Comp. Strength at 28 days	Maximum Water-Cement Ratio					sistency a. Slump	Cement Content				
		Air-Entrained Concrete		Non Air- Entrained Concrete		Vibrated	Non- Vibrated	Vibrated		Non- Vibrated		
		Rounded Aggregate	Angular Aggre- gate	Rounded Aggregate	Angular Aggre- gate	Vib	Z QII	Min.	Max.	Min.	Max.	
Units	psi	:	<b></b>		1	inch	inch	lb/cy	lb/cy	, lb/cy	! lb/cy	
AA	4,500	0.381	0.426	-	-	3.5	i _	639	715	· -	! -	
AA Slip Form	4,500	0.381	0.426	-	-	1.5	-	639	715	: :	-	
Drilled Pier	4,500	:	-	0.450	0.450	-	5-7 dry 7-9 wet	_	-	640	800	
Α	3,000	0.488	0.532	0.550	0.594	3.5	4	564	! -	602	! -	
В	2,500	0.488	0.567	0.559	0.630	2.5	4	508	T -	. 545	-	
B Slip Formed	2,500	0.488	0.567	-	-	1.5	-	508	-	-	-	
Sand Light- weight	4,500	-	0.420	_	: -	4	· ·	715	-		_	
Latex Modified	3,000 7 day	0.400	0.400	-	: -	6	· -	658	-	·	-	
Flowable Fill excavatable	150 max. at 56 days	as needed	as needed	as needed	as needed	-	Flow- able	- -	-	40	100	
Flowable Fill non-excavatable	125	as needed	· as needed	as needed	; as needed	- -	Flow- able	-	-	100	as needed	
Pavement	4,500 design, field 650 flexural, design only	0.559	0.559	-	1 1 1 1 1 1	1.5 slip form 3.0 hand place		526	-	*		
Precast	See Table 1077-1	as needed	as needed	-	[  -  -	6	as needed	as needed	as needed	as needed	as needed	
Prestress	per contract	See Table 1078-1	See Table 1078-1	-	• •	8	-	564	as needed		-	

Page 10-65, Article 1050-1, GENERAL, line 41, replace the first sentence with:

All fencing material and accessories shall meet Section 106.

Page 10-23, Table 1005-1, AGGREGATE GRADATION-COARSE AGGREGATE, replace with the following:

Light- weight <sup>C</sup>	ABC (M)	ABC	9	14M	78M	67	. 6M	57M	57	5	467M	4	Std. Size#	and the second section of the second section is an arrange section of the second section is a second section of the section of t	a came d'antideren a seconda anque
	1	:		ı						-	100	100	2"		AG
	100	100	ı	: :	ı	:	· · ·	100	100	100	95- 100	90- 100	1 1/2"		
ı	75- 100	75- 97	ı	ı	·	100	100	95- 100	95- 100	90-	: 1	20- 55	1"		
i . '		:	ı		100	90-	100			20- 55	35- 70	0-15	3/4"	PRO 1 N. A. 100 Lanese W. 1.1.	GRE
100	45- 79	55- 80	ı	. 1	98-		20- 55	25- 45	25- 60	0-10		. 1	1/2"	Perce	SATE
100			100	100	75- 100	20- 55	0-20			0-5	0-30	0-5	3/8"	Percentage of Total by Weight Passing	AGGREGATE GRADATION - COARSE AGGREGATE
5- 40	20- 40	35- 55	85- 100	35- 70	20- 45	0-10	0-8	0-10	0-10		0-5		#		
0-20		; ;	10 <u>-</u> 40	5-20	0-15	0-5		0-5	0-5		ı	ı	#8		
	0- 25	25- 45		ı		1			ı		1	• :	#10		OARS
0-10		: I	0-10	0-8		•		•	ı	•	ı	ı	#16	Passin	E AGO
	. 1	14- 30		ı	: '	ı	!	1	ı	ı	•	•	#40	OFG.	GREG
0-2.5	0- 12 <sup>B</sup>	4- 12 <sup>B</sup>	➣	<b>.</b>	: <b>&gt;</b>	A	, <b>&gt;</b>	<b>A</b>	>	<b>&gt;</b>	A	<b>&gt;</b> ,	#200		ATE
AST	1aintenance Stabi	Aggregate Base Course, Aggregate Stabilization	AST	Asphalt Plant Mix, AST, Weep Hole Drains, Str. Concrete	Asphalt Plant Mix, AST, Str. Conc, Weep Hole Drains	AST, Str. Concrete, Asphalt Plant Mix	AST	AST, Concrete Pavement	AST, Str. Concrete, Shoulder Drain, Sediment Control Stone	AST, Sediment Control Stone	Asphalt Plant Mix	Asphalt Plant Mix	Remarks		

Page 10-115, Subarticle 1074-7(B), Gray Iron Castings, lines 10-11, replace with the first two sentences with the following:

Supply gray iron castings meeting all facets of AASHTO M 306 excluding proof load. Proof load testing will only be required for new casting designs during the design process, and conformance to M306 loading (40,000 lbs.) will be required only when noted on the design documents.

Page 10-126, Table 1078-1, REQUIREMENTS FOR CONCRETE, replace with the following:

TABLE 1078-1 REQUIREMENTS FOR CONCRETE								
Property	28 Day Design Compressive Strength 6,000 psi or less	28 Day Design Compressive Strength greater than 6,000 psi						
Maximum Water/Cementitious Material Ratio	0.45	0.40						
Maximum Slump without HRWR	3.5"	3.5"						
Maximum Slump with HRWR	8"	8"						
Air Content (upon discharge into forms)	5 + 2%	5 + 2%						

Page 10-151, Article 1080-4 Inspection and Sampling, lines 18-22, replace (B), (C) and (D) with the following:

- (B) At least 3 panels prepared as specified in 5.5.10 of AASHTO M 300, Bullet Hole Immersion Test.
- (C) At least 3 panels of 4"x6"x1/4" for the Elcometer Adhesion Pull Off Test, ASTM D4541.
- (D) A certified test report from an approved independent testing laboratory for the Salt Fog Resistance Test, Cyclic Weathering Resistance Test, and Bullet Hole Immersion Test as specified in AASHTO M 300.
- (E) A certified test report from an approved independent testing laboratory that the product has been tested for slip coefficient and meets AASHTO M253, Class B.

Page 10-162, Subarticle 1081-1(A) Classifications, lines 4-7, delete the second and third sentences of the description for Type 3A.

Page 10-162, Subarticle 1081-1(B) Requirements, lines 26-30, replace the second paragraph with the following:

For epoxy resin systems used for embedding dowel bars, threaded rods, rebar, anchor bolts and other fixtures in hardened concrete, the manufacturer shall submit test results showing that the

bonding system will obtain 125% of the specified required yield strength of the fixture. Furnish certification that, for the particular bolt grade, diameter and embedment depth required, the anchor system will not fail by adhesive failure and that there is no movement of the anchor bolt. For certification and anchorage, use 3,000 psi as the minimum Portland cement concrete compressive strength used in this test. Use adhesives that meet Section 1081.

List the properties of the adhesive on the container and include density, minimum and maximum temperature application, setting time, shelf life, pot life, shear strength and compressive strength.

Page 10-169, Subarticle 1081-3(G) Anchor Bolt Adhesives, delete this subarticle.

Page 10-179, Subarticle 1087-4(A) Composition, lines 39-41, replace the third paragraph with the following:

All intermixed and drop-on glass beads shall not contain more than 75 ppm arsenic or 200 ppm lead.

Page 10-180, Subarticle 1087-4(B) Physical Characteristics, line 8, replace the second paragraph with the following:

All intermixed and drop-on glass beads shall comply with NCGS § 136-30.2 and 23 USC § 109(r).

Page 10-181, Subarticle 1087-7(A) Intermixed and Drop-on Glass Beads, line 24, add the following after the first paragraph:

Use X-ray Fluorescence for the normal sampling procedure for intermixed and drop-on beads, without crushing, to check for any levels of arsenic and lead. If any arsenic or lead is detected, the sample shall be crushed and repeat the test using X-ray Fluorescence. If the X-ray Fluorescence test shows more than a LOD of 5 ppm, test the beads using United States Environmental Protection Agency Method 6010B, 6010C or 3052 for no more than 75 ppm arsenic or 200 ppm lead.

Page 10-204, Subarticle 1092-2(A) Performance and Test Requirements, replace
Table 1092-3 Minimum Coefficient of Retroreflection for NC Grade A with the following:

TABLE 1092-3 MINIMUM COEFFICIENT OF RETROREFLECTION FOR NC GRADE A (Candelas Per Lux Per Square Meter)											
Observation Angle, degrees	Entrance Angle, degrees	White	Yellow	Green	Red	Blue	Fluorescent Yellow Green	Fluorescent Yellow			
0.2	-4.0	525	395	52	95	30	420	315			
0.2	30.0	215	162	22	43	10	170	130			
0.5	-4.0	310	230	31	- 56	18	245	185			
0.5	30.0	135	100	14	27	6	110	81			
1.0	-4.0	120	60	8	16	3.6	64	48			
1.0	30.0	45	34	4.5	9	2	36	27			

## TRUCK MOUNTED CHANGEABLE MESSAGE SIGNS:

(8-21-12) 1101.

SP11 R10

Revise the 2012 Roadway Standard Drawings as follows:

**Drawing No. 1101.02, Sheet 12, TEMPORARY LANE CLOSURES,** replace General Note #11 with the following:

- 11- TRUCK MOUNTED CHANGEABLE MESSAGE SIGNS (TMCMS) USED ON SHADOW VEHICLES FOR "IN LANE" ACTIVITIES SHALL BE A MINIMUM OF 43" X 73". THE DISPLAY PANEL SHALL HAVE FULL MATRIX CAPABILITY WITH THE CAPABILITY TO PROVIDE 2 MESSAGE LINES WITH 7 CHARACTERS PER LINE WITH A MINIMUM CHARACTER HEIGHT OF 18". FOR ADDITIONAL MESSAGING, CONTACT THE WORK ZONE TRAFFIC CONTROL SECTION.
- 12- TMCMS USED FOR ADVANCED WARNING ON VEHICLES LOCATED ON THE SHOULDER MAY BE SMALLER THAN 43" X 73". THE DISPLAY PANEL SHALL HAVE THE CAPABILITY TO PROVIDE 2 MESSAGE LINES WITH 7 CHARACTERS PER LINE WITH A MINIMUM CHARACTER HEIGHT OF 18". FOR ADDITIONAL MESSAGING, CONTACT THE WORK ZONE TRAFFIC CONTROL SECTION.

**Drawing No. 1101.02, Sheet 13, TEMPORARY LANE CLOSURES,** replace General Note #12 with the following:

12- TRUCK MOUNTED CHANGEABLE MESSAGE SIGNS (TMCMS) USED ON SHADOW VEHICLES FOR "IN LANE" ACTIVITIES SHALL BE A MINIMUM OF 43" X 73". THE DISPLAY PANEL SHALL HAVE FULL MATRIX CAPABILITY WITH THE CAPABILITY TO PROVIDE 2 MESSAGE LINES WITH 7 CHARACTERS PER LINE WITH A MINIMUM CHARACTER HEIGHT OF 18". FOR ADDITIONAL MESSAGING, CONTACT THE WORK ZONE TRAFFIC CONTROL SECTION.

13- TMCMS USED FOR ADVANCED WARNING ON VEHICLES LOCATED ON THE SHOULDER MAY BE SMALLER THAN 43" X 73". THE DISPLAY PANEL SHALL HAVE THE CAPABILITY TO PROVIDE 2 MESSAGE LINES WITH 7 CHARACTERS PER LINE WITH A MINIMUM CHARACTER HEIGHT OF 18". FOR ADDITIONAL MESSAGING, CONTACT THE WORK ZONE TRAFFIC CONTROL SECTION.