### **PROJECT SPECIAL PROVISIONS**

#### **ROADWAY**

#### **SHOULDER RECONSTRUCTION:**

(1-18-00) (Rev. 6-19-07)

RR07 Rev.

#### Description

The work covered by this provision consists of reconstructing earth shoulders in accordance with the *Roadway Standard Drawing Nos.* 560.01 and 560.02, from the edge of pavement to the existing shoulder point as directed by the Engineer. Perform this work immediately after the resurfacing operations are completed as directed by the Engineer.

#### Materials

On any map that contains widening, use all suitable material generated from the widening operation to construct the shoulder. Furnish any other earth material necessary for the construction of the shoulders. Provide earth material meeting the approval of the Engineer. No testing will be necessary.

#### **Construction Methods**

Perform shoulder reconstruction in the following order: scarify the existing shoulder to provide the proper bond; add the earth material to the shoulder; and compact the reconstructed shoulder to the satisfaction of the Engineer.

The Contractor shall dispose of any excess material generated by the shoulder reconstruction in an approved disposal site.

#### Measurement and Payment

Shoulder Reconstruction will be measured and paid for as the actual number of shoulder miles, including median shoulder, that have been constructed. Measurement will be made along the edge of each shoulder. Measurement will be made to the nearest 0.01 of a mile. Such price and payment will be full compensation for furnishing earth material, hauling, placing, compaction, seeding and mulching and all incidentals necessary to complete construction of the shoulders.

*Incidental Stone Base* will be measured and paid for as provided in Article 545-6 of the *Standard Specifications*.

Payment will be made under:

Pay Item
Shoulder Reconstruction

Pay Unit Shoulder Mile

#### FINAL ACCEPTANCE AND FOURTEEN DAY OBSERVATION PERIOD:

(7-1-95)

R1 R13

Upon completion of construction as shown on each map, a 14 day observation period is required before acceptance. During the 14-day period, warrant the resurfaced area against failure.

No payment will be made for replacing failed pavement, as the cost of it will be considered incidental to the work initially paid for under the various items in the contract.

Completion and final acceptance of the project is contingent upon successful completion of the Observation Period. The observation period will be considered a part of the work required to be completed by the final completion date specified herein.

#### **INCIDENTAL STONE BASE:**

(7-1-95) (Rev.7-18-06)

R5 R28

#### Description

Place incidental stone base on driveways, mailboxes, etc. immediately after paving and do not have the paving operations exceed stone base placement by more than one week without written permission of the Engineer.

#### **Materials and Construction**

Provide and place incidental stone base in accordance with the requirements of Section 545 of the 2006 Standard Specifications.

#### **Measurement and Payment**

*Incidental Stone Base* will be measured and paid for in accordance with Article 545-6 of the 2006 Standard Specifications.

# **MILLING ASPHALT PAVEMENT:**

Revise the 2006 Standard Specifications as follows:

Page 6-6, Article 607-3, add the following after the third sentence of the fourth paragraph:

Any leveling or patching NOT due to the Contractor's negligence shall be repaired with hot asphalt plant mix and will be paid for under the appropriate line item for leveling or patching.

#### **ASPHALT PAVEMENTS - SUPERPAVE:**

(7-18-06) (Rev 9-19-06)

R6 R01

Revise the 2006 Standard Specifications as follows:

# Page 6-2, Article 600-9 Measurement and Payment

Delete the second paragraph.

Page 6-12, 609-5(C)2(c) add after (AASHTO T 209):

or ASTM D 2041

Page 6-13, last line on page & Page 6-14, Subarticle 609-5(C)(2)(e), delete and substitute the following:

- (e) Retained Tensile Strength (TSR) (AASHTO T 283 Modified), add subarticle (1) Option 1 before the first paragraph.
  - (1) Option 1

Add subarticle (2) Option 2 and the following sentence as the first sentence of the second paragraph:

(2) Option 2

Mix sampled from truck at plant with one set of specimens prepared by the Contractor and then tested jointly by QA and QC at a mutually agreed upon lab site within the first 7 calendar days after beginning production of each new mix design.

Page 6-28, 610-3(A) Mix Design-General, third sentence of the fourth paragraph:

Substitute 20% for 15%

First, second and third sentences of the fifth paragraph:

Substitute 20% for 15%

Page 6-44, 610-8, third full paragraph, replace the first sentence with the following:

Use the 30 foot minimum length mobile grade reference system or the non-contacting laser or sonar type ski with at least four referencing stations mounted on the paver at a minimum length of 24 feet to control the longitudinal profile when placing the initial lanes and all adjacent lanes of all layers, including resurfacing and asphalt in-lays, unless otherwise specified or approved.

# Page 6-54, Article 620-4, add the following pay item:

Pay Item

Pay Unit

Asphalt Binder for Plant Mix, Grade PG 70-28

Ton

# Page 6-69, Table 660-1 Material Application Rates and Temperatures, add the following:

<b>Type of Coat</b>	Grade of Asphalt	Asphalt Rate	Application Temperature °F	Aggregate Size	Aggregate Rate lb./sq. vd. Total
Sand Seal	CRS-2 or CRS-2P	<b>gal/yd²</b> 0.22-0.30	150-175	Blotting Sand	12-15

# Page 6-75, 660-9(B), add the following as sub-item (5)

#### (5) Sand Seal

Place the fully required amount of asphalt material in one application and immediately cover with the seal coat aggregate. Uniformly spread the fully required amount of aggregate in one application and correct all non-uniform areas prior to rolling.

Immediately after the aggregate has been uniformly spread, perform rolling.

When directed, broom excess aggregate material from the surface of the seal coat.

When the sand seal is to be constructed for temporary sealing purposes only and will not be used by traffic, other grades of asphalt material meeting the requirements of Articles 1020-6 and 1020-7 may be used in lieu of the grade of asphalt required by Table 660-1 when approved.

Page 10-41, Table 1012-1, add the following:

	Mix	Course Aggregate	]	Fine Aggregate Angularity	S	and Equivalent	Flat & Elongated 5:1
	Type	Angularity (b) ASTM		% Minimum AASHTO		% Minimum	Ratio % Maximum
		D5821		T304 Method A		AASHTO T176	ASTM D4791 Section 8.4
: :	S 9.5 D	100/100		45		50	10

Page 10-45, Replace Table 1012-2 with the following:

TABLE 1012-2 NEW SOURCE RAP GRADATION and BINDER TOLERANCES

(Apply Tolerances to Mix Design Data)

Mix Type	0-20% RAP		21-25% RAP			26%+ RAP			
Sieve (mm)	Base	Inter.	Surf.	Base	Inter.	Surf.	Base	Inter.	Surf.
$P_{b}$ %		± 0.7%			$\pm 0.4\%$			± 0.3%	
1 1/2"	±10	-	-	±7	-	-	±5	-	<u>-</u>
(37.5)				:					
3/4"	±10	$\pm 10$	-	±7	±7	-	±5	±5	-
(19.0)									10
1/2"	-	±10	±6	-	±7	±3	-	±5	±2
(12.5)			1.0						±4
3/8" (9.5)	-	-	±8	. <b>-</b>	-	±5	-	_	<u></u> +
No. 4	±10	-	±10	±7	: : :	±7	±5	-	±5
(4.75)									
No. 8	±8	±8	±8	±5	±5	±5	±4	±4	±4
(2.36)									
No.16	±8	±8	±8	±5	±5	±5	<u>±</u> 4	±4	±4
(1.18)		1.0				1.5	. 4	1.4	
No. 30	±8	<u>±8</u>	±8	±5	±5	±5	±4	±4	±4
(0.600) No. 50	_	_	±8	. <b>-</b>	<u>-</u>	±5	_	_	±4
(0.300)			0						
No. 200 (0.075)	±4	±4	<u>±</u> 4	±2	±2	±2	±1.5	±1.5	±1.5

# **ASPHALT BINDER CONTENT OF ASPHALT PLANT MIXES:**

(1-1-02)

R6 R15

The approximate asphalt binder content of the asphalt concrete plant mixtures used on this project will be as follows:

Type B 25.0	4.3 %
Type I 19.0	4.7 %
Type S 4.75A	7.0 %
Type SF 9.5A	6.5 %
Type S 9.5	6.0 %
Type S 12.5	5.5 %
	Type S 4.75A Type SF 9.5A Type S 9.5

The actual asphalt binder content will be established during construction by the Engineer within the limits established in the 2006 Standard Specifications.

### PRICE ADJUSTMENT - ASPHALT BINDER FOR PLANT MIX:

(11-21-00)

R6 R25

Price adjustments for asphalt binder for plant mix will be made in accordance with Section 620 of the 2006 Standard Specifications.

The base price index for asphalt binder for plant mix is \$ 318.93 per ton.

This base price index represents an average of F.O.B. selling prices of asphalt binder at supplier's terminals on **October 1, 2007**.

#### ASPHALT CONCRETE SURFACE COURSE COMPACTION:

(7-1-95)

R6 R49

Compact the asphalt surface course on this project in accordance with Subarticle 610-9 of the 2006 Standard Specifications and the following provision:

Perform the first rolling with a steel wheel roller followed by rolling with a self-propelled pneumatic tired roller with the final rolling by a steel wheel roller.

#### **RESURFACING EXISTING BRIDGES:**

(7-1-95)

R6 R61

The Contractor's attention is directed to the fact that he will be required to resurface the bridges on this project if directed by the Engineer.

Place the surface so as to follow a grade line set by the Engineer with the minimum thickness as shown on the sketch herein or as directed by the Engineer. State Forces will make all necessary repairs to the bridge floors prior to the time that the Contractor places the proposed surfacing. Give the Engineer at least 15 days notice prior to the expected time to begin operations so that State Forces will have sufficient time to complete their work.

At all bridges that are not to be resurfaced, taper out the proposed resurfacing layer adjacent to the bridges to insure a proper tie-in with the bridge surface.

#### **PAVEMENT WIDTH VARIES:**

(7-1-95

R6 R76

The Contractor's attention is directed to the fact that the existing pavement varies in width and the Contractor will be required to widen the pavement as directed by the Engineer in order to obtain a uniform edge of pavement.

# ASPHALT CONCRETE SURFACE COURSE, TYPE xxx (Leveling Course):

(7-1-95) R6 R85

Place a leveling course of Asphalt Concrete Surface Course, Type \_\_\_\_ at locations shown on the sketch maps and as directed by the Engineer. The rate of this leveling course is not established but will be determined by allowing the screed to drag the high points of the section. It is anticipated that some map numbers will be leveled from beginning to end while others may only require a leveling course for short sections.

The Asphalt Concrete Surface Course, Type \_\_ (Leveling Course) shall meet the requirements of Section 610 of the *Standard Specifications* except payment will be made at the contract unit price per ton for *Asphalt Concrete Surface Course*, *Type* \_\_ (Leveling Course).

#### **PATCHING EXISTING PAVEMENT:**

(1-15-02)

(R6R88 Rev.)

#### Description:

The Contractor's attention is directed to the fact that there are areas of existing pavement on this project that will require repair prior to resurfacing.

Patch the areas that, in the opinion of the Engineer, need repairing. The areas to be patched will be delineated by the Engineer prior to the Contractor performing repairs.

## Construction Methods:

The patching consists of Asphalt Concrete Base Course, Asphalt Concrete Intermediate Course, Asphalt Concrete Surface Course, or a combination of base, binder and surface course, and pavement removal, as directed by the Engineer.

The Contractor's attention is directed to the fact that all patching of existing pavement performed under this contract shall be performed with the use of a milling machine. This machine shall have a minimum cutting width of 36", be of sufficient size and capacity to perform the work. The machine shall have been designed and built exclusively for pavement milling operations and shall have sufficient power, traction and stability to accurately maintain depth of cut and slope. Multiple passes may be required to remove deteriorated pavement.

Milling width and depth will be varied by the Engineer's representative to accomplish desired results. Payment will be made for the area delineated by the Engineer. Any overages resulting from equipment limitations will not be compensated.

Patching of existing pavement includes but is not limited to the **milling** of the existing pavement to a neat vertical joint and uniform line; the removal and disposal of pavement, base, and subgrade material as approved or directed by the Engineer; the coating of the area to be repaired with a tack coat; and the replacement of the removed material with asphalt plant mix.

Place Asphalt Concrete Base Course, in lifts not exceeding 5 1/2 inches. Utilize compaction equipment suitable for compacting patches as small as 3.5 feet by 6 feet on each lift. Use an approved compaction pattern to achieve proper compaction. If patched pavement is to be open to traffic for more than 48 hours prior to overlay, then use Asphalt Surface Course in the top 1.25 inches of the patch.

Remove existing pavement at locations directed by the Engineer in accordance with Section 250 of the Standard Specifications.

Schedule operations so that all areas where pavement has been removed will be repaired on the same day of the pavement removal, and all lanes of traffic restored.

#### Method of Measurement:

The quantity of patching existing pavement to be paid for will be the actual number of tons of asphalt plant mix, complete in place, which has been used to make completed and accepted repairs. The asphalt plant mixed material will be measured by being weighed in trucks on certified platform scales or other certified weighing devices.

#### Basis of Payment:

The quantity of patching existing pavement, measured as provided above, will be paid for at the contract unit price per ton for "Patching Existing Pavement".

The above price and payment will be full compensation for all work covered by this provision, including but not limited to removal and disposal of pavement; furnishing and applying tack coat; furnishing, placing, and compacting of asphalt plant mix; furnishing of asphalt binder for the asphalt plant mix; and furnishing scales.

Any provisions included in the contract in the form of project special provisions or in any other form which provide for adjustments in compensation due to variations in the price of asphalt binder will not be applicable to payment for the work covered by this provision.

The item of "Patching Existing Pavement" will be considered to be a minor item. In the event that the item of "Patching Existing Pavement" overruns the original bid quantity by more than 100 percent, the provisions of Article 104-5 pertaining to revised contract unit price for overrunning minor items will not apply to this item.

Payment will be made under:	
Patching Existing Pavement	Ton

# **ADJUSTMENT OF MANHOLES, METER BOXES, AND VALVE BOXES:**

(7-1-95)

R8 R97 (Rev.)

The Contractor's attention is directed to Article 858-3 of the 2006 Standard Specifications. Cast iron or steel fittings will not be permitted for the adjustment of manholes, meter boxes, and valve boxes on this project.

Prior to the placement of S9.5B, all manhole rings and valve and meter boxes shall be removed and the area covered with a steel plate (s) capable of carrying traffic. Once the S9.5B Asphalt has been placed the steel plate shall be removed and the manhole ring set to finish grade of the new pavement. No direct payment will be made for steel plates. The cost of this work will be incidental to adjustment of manholes, meter boxes and valve boxes.

All manholes shall be completed within fourteen (14) calendar days from the time the S9.5B Pavement is completed.

#### **AGGREGATE PRODUCTION:**

(11-20-01) (Rev. 11-21-06)

R10 R05

Provide aggregate from a producer who uses the current Aggregate Quality Control/Quality Assurance Program which is in effect at the time of shipment.

No price adjustment is allowed to contractors or producers who use the program. Participation in the program does not relieve the producer of the responsibility of complying with all requirements of the 2006 Standard Specifications. Copies of this procedure are available upon request from the Materials and Test Unit.

# **CONCRETE BRICK AND BLOCK PRODUCTION:**

(11-20-01) (Rev. 11-21-06)

R10 R10

Provide concrete brick and block from a producer who uses the current Solid Concrete Masonry Brick/Unit Quality Control/Quality Assurance Program that is in effect on the date that material is received on the project.

No price adjustment is allowed to contractors or producers who use the program. Participation in the program does not relieve the producer of the responsibility of complying with all requirements of the 2006 Standard Specifications. Copies of this procedure are available upon request from the Materials and Test Unit.

# **PORTLAND CEMENT CONCRETE (Alkali-Silica Reaction):**

2-20-01

R10 R16

Revise the 2006 Standard Specifications as follows:

**Article 1024-1(A)**, replace the 2nd paragraph with the following:

Certain combinations of cement and aggregate exhibit an adverse alkali-silica reaction. The alkalinity of any cement, expressed as sodium-oxide equivalent, shall not exceed 1.0 percent. For mix designs that contain non-reactive aggregates and cement with an alkali content less than 0.6%, straight cement or a combination of cement and fly ash, cement and ground granulated blast furnace slag or cement and microsilica may be used. The pozzolan quantity shall not exceed the amount shown in Table 1024-1. For mixes that contain cement with an alkali content between 0.6% and 1.0%, and for mixes that contain a reactive aggregate documented by the Department, regardless of the alkali content of the cement, use a pozzolan in the amount shown in Table 1024-1.

Obtain the list of reactive aggregates documented by the Department at:http://www.ncdot.org/doh/operations/materials/pdf/quarryasrprob.pdf

# Table 1024-1 Pozzolans for Use in Portland Cement Concrete

Pozzolan	Rate		
Class F Fly Ash	20% by weight of required cement content, with 1.2		
	lbs Class F fly ash per lb of cement replaced		
Ground Granulated Blast Furnace Slag	35%-50% by weight of required cement content		
	with 1 lb slag per lb of cement replaced		
Microsilica	4%-8% by weight of required cement content, with		
	1 lb microsilica per lb of cement replaced		

#### **GLASS BEADS:**

(7-18-06)

R10 R35

Revise the 2006 Standard Specifications as follows:

#### Page 10-223, 1087-4(C) Gradation & Roundness

Replace the second sentence of the first paragraph with the following:

All Drop-On and Intermixed Glass Beads shall be tested in accordance with ASTM D1155.

Delete the last paragraph.

# **CHANGEABLE MESSAGE SIGNS**

 $\overline{(11-21-06)}$ 

R11 R11

Revise the 2006 Standard Specifications as follows:

# Page 11-9, Article 1120-3, Replace the 3rd sentence with the following:

Sign operator will adjust flash rate so that no more than two messages will be displayed and be legible to a driver when approaching the sign at the posted speed.

# **PAVEMENT MARKING LINES:**

(11-21-06) (Rev. 9-18-07)

RR12R01

Revise the 2006 Standard Specifications as follows:

Page 12-2, 1205-3(D) Time Limitations for Replacement, add the following at the beginning of the chart:

Facility Type	Marking Type	Replacement Deadline				
Full-control-of-access multi-lane roadway (4 or more total lanes) and ramps, including Interstates	including	By the end of each workday's operation if the lane is opened to traffic				

Page 12-14, Subarticle 1205-10, Measurement and Payment, delete the first sentence of the first paragraph and replace with the following:

Pavement Marking Lines will be measured and paid for as the actual number of linear feet of pavement marking lines per application that has been satisfactorily placed and accepted by the Engineer.