

BUILD-UP AND
SPIRAL REINFORCING

PRESTRESS STRAND (TYP.)

2"CL.
TYP.

2"CL.
TYP.

1"Ø FIELD DRILLED
HOLE (TYP.) W/ *6 DOWEL.

SECTION "B-B"

(AT THE CONTRACTOR'S OPTION, PILE BUILD-UP MAY BE CONSTRUCTED WITH DOWELS.)

DOWEL INSTALLATION FOR OPTIONAL BUILD-UP

GROUT COMPRESSIVE STRENGTH: f'c= 5,000 PSI

BEFORE DRILLING DOWEL HOLES, REMOVE THE UPPER 3"OF CONCRETE FROM THE TOP OF THE PILE WITHOUT DAMAGE TO THE REINFORCING STEEL. THE REMOVAL PLANE SHOULD BE NORMAL TO THE EDGE OF THE PILE.

DOWEL HOLES SHALL BE POSITIONED TO MAINTAIN 1/2" CLEAR TO ALL EXISTING PRESTRESSING STRANDS IN THE CONCRETE PILE.


FIELD DRILLED HOLES SHALL BE CLEAN AND FREE OF ANY OBSTRUCTIONS BEFORE GROUTING OF DOWELS. DOWEL BARS SHALL BE INSTALLED AND GROUTED WITH AN APPROVED NON-SHRINK GROUT.

THE SPIRAL REINFORCING IN ALL BUILD-UPS SHALL BE W4.0 COLD DRAWN WIRE WHICH SHALL BE SECURED TO THE LONGITUDINAL REINFORCEMENT TO MAINTAIN PITCH.


THE SPIRAL REINFORCING IN THE BUILD-UP AND THE PRESTRESSED CONCRETE PILE SHALL BE SPLICED BY OVERLAPPING A MIN. OF ONE TURN.


TYPICAL SECTION TYPICAL SECTION TYPICAL SECTION TYPICAL PATTERN FOR BURNING STRANDS

1/2" OR 0.6" Ø GRADE 270 L.R. PRESTRESS STRANDS



1/2" OR 0.6" Ø GRADE 270 L.R. PRESTRESS STRANDS





PICK-UP POINTS

QUANTITIES FOR ONE 12" PRESTRESSED PILE						
	CONCRETE	PILE WT.	ONE POINT PICK-UP		TWO POINT PICK-UP	
LENGTH	CU. YDS.	TONS	0.300L	0.700L	0.207L	0 . 586L
25′-0′′	0.91	1.85	7′-6′′	17'-6''		
30′-0′′	1.10	2.22	9'-0''	21'-0''		
35′-0′′	1.28	2 . 59	10'-6''	24'-6''		
40'-0''	1.46	2.96	12'-0''	28'-0''		
45'-0''	1.64	3 . 33	13'-6''	31'-6''		
50′-0′′	1.83	3.72	15'-0''	35′-0′′		
55′-0′′	2.01	4.09			11'-41/2''	32′-3′′
60′-0′′	2.19	4.46			12′-5′′	35′-2′′
65′-0′′	2.38	4. 81			13′-51/2′′	38′-1′′
70′-0′′	2 . 57	5 . 18			14'-6''	41'-0''

NOTES

PRESTRESSED CONCRETE STRENGTH : f'c = 7,500 PSI
BUILD-UP CONCRETE STRENGTH : f'c = 7,500 PSI

STRAND DATA:

SIZE	GRADE	AREA	ULTIMATE STRENGTH	APPLIED PRESTRESS FORCE
1/2′′	270 L.R.	0.153	41,300# PER STRAND	30,980# PER STRAND
0.6"	270 L.R.	0.217	58,600# PER STRAND	43,940# PER STRAND

ALL PRESTRESSING STRANDS SHALL BE 7-WIRE LOW-RELAXATION GRADE 270 STRANDS CONFORMING TO AASHTO M203. STRAND SAMPLING REQUIREMENTS SHALL BE IN ACCORDANCE WITH THE STANDARD SPECIFICATIONS.

AT THE CONTRACTOR'S OPTION, 1/2" OR 0.6" STRANDS MAY BE USED IN EITHER THE 4 OR 5 STRAND CONFIGURATION SHOWN IN THE TYPICAL SECTION DETAIL. MIXING OF STRAND SIZE IS NOT ALLOWED.

THE SLIP-FORM METHOD OF CASTING PILES WILL NOT BE PERMITTED.

TRANSFER THE LOAD FROM THE ANCHORAGES TO THE PILE AFTER THE CONCRETE HAS ATTAINED A MINIMUM COMPRESSIVE STRENGTH OF 4,000 PSI.

IF STRAND STRESS IS RELIEVED BY BURNING, THE STRANDS SHALL BE BURNED IN PAIRS, EXCEPT WHERE 5 STRANDS ARE USED, THE LAST STRAND MAY BE BURNED SINGLY ACCORDING TO BURNING PATTERNS SHOWN. NOT MORE THAN 4 STRANDS MAY BE BURNED AT ANY ONE SECTION BEFORE THE SAME STRANDS ARE BURNED AT BOTH ENDS OF THE BED AND BETWEEN EACH PAIR OF PILES IN THE BED.

PROPOSED DEVICES FOR LIFTING PILES, RECESS DETAILS, AND PATCHING MATERIAL SHALL BE DETAILED IN SHOP DRAWINGS. AFTER ATTACHMENTS HAVE BEEN REMOVED, OPENINGS SHALL BE REPAIRED SUCH THAT THE APPEARANCE OF THE PILE IS UNIFORM.

WHERE CAST-IN-PLACE LIFTING DEVICES ARE NOT USED, PICK-UP POINTS ARE TO BE INDICATED WITH A 2" WIDE BLACK MARK.

DRIVE PILES USING A METHOD APPROVED BY THE ENGINEER, WHEREBY THE HEAD OF THE PILE IS NOT DAMAGED.

DRIVING OF THE BUILT-UP PILE WILL NOT BE PERMITTED UNTIL THE CONCRETE HAS REACHED A COMPRESSIVE STRENGTH OF 5,000 PSI AND UNTIL A PERIOD OF SEVEN DAYS HAS ELAPSED SINCE CASTING OF THE BUILD-UP.

THE WATER/CEMENT RATIO FOR PRESTRESSED CONCRETE PILES SHALL NOT EXCEED 0.40.

ALL BAR SUPPORTS USED IN THE PRESTRESSED CONCRETE PILES, AND ALL INCIDENTAL REINFORCING STEEL SHALL BE EPOXY COATED IN ACCORDANCE WITH THE STANDARD SPECIFICATIONS.

PRESTRESSED CONCRETE PILES SHALL CONTAIN CALCIUM NITRITE CORROSION INHIBITOR IN ACCORDANCE WITH THE STANDARD SPECIFICATIONS.

THE CONCRETE IN THE PRESTRESSED CONCRETE PILES SHALL CONTAIN SILICA FUME. SILICA FUME SHALL BE SUBSTITUTED FOR 5% OF THE PORTLAND CEMENT BY WEIGHT. IF THE OPTION OF ARTICLE 1024-1 OF THE STANDARD SPECIFICATIONS TO PARTIALLY SUBSTITUTE CLASS F FLY ASH FOR PORTLAND CEMENT IS EXERCISED, THEN THE RATE OF FLY ASH SUBSTITUTION SHALL BE REDUCED TO 1.0 LB OF FLY ASH PER 1.0 LB. NO PAYMENT WILL BE MADE FOR THIS SUBSTITUTION AS IT IS CONSIDERED INCIDENTAL TO THE VARIOUS PAY ITEMS.

PROJECT NO. _____B-4598 ______PAMLICO _____ COUNTY STATION: ____16+43.00 -L-

SHEET 5 OF 5



NOTES FOR — CORROSION

PROTECTION

DEPARTMENT OF TRANSPORTATION
RALEIGH

STANDARD

12" PRESTRESSED CONCRETE PILE END BENT No.1 & 2

884E46B8CE5B4B6 4/18/2017					
OCUMENT NOT CONSIDERED	NO.				
FINAL UNLESS ALL	1				
SIGNATURES COMPLETED	2				

END BENT NO. I & Z

SHEET N

CONSIDERED

NO. BY: DATE: NO. BY: DATE:

TOTAL

CHECKED BY: A. SORSENGINH DATE: 9/20/16

DRAWN BY: FCJ 7/88 REV. II/30/IO REV. IO/I/II MAA/GM MAA/TMG

CHECKED BY: CRK 3/89 REV. I2/I4 MAA/TMG

ASSEMBLED BY: M.M. AHMED DATE: 9/1/16